FILM SPECIFICATIONS

Seal/Application Temperature (Sealant layer)

Seal Strength (Self-to-self, sealant layer)

OTR (Oxygen Transmission Rate)

Film Shelf Life

WVTR (Water Vapor Transmission Rate)

Storage Temperature Range

Storage Humidity Range

THICK GAUGE METALLIZED GLOSS — Pouches & Rollstock

DESCRIPTION	This film is ideal for durable applications requiring oxygen/moisture barrier properties and puncture resistance. Metallized film will create a metallic silver package interior, and can also create metallic color effects in printed artwork. Gloss finish has high shine, and minimal color distortion of printed artwork. Gloss metallized film will give metallic artwork a "polished metal"-like finish.			
	Evaluation and fitness-for-use is the sole responsibility of the customer.			
STRUCTU	Composite: 4.8mil 3-layer laminated film Laminate (Exterior) Layer: 1.2mil gloss PET (Polyethylene Terephthalate) Print Surface Layer: 48ga CT MET-PET (Corona-Treated Metallized PET)			
	Sealant (Interior) Layer: 3.0mil clear mLLDPE (Metallocene Linear Low-Density Polyethylene)			
FEATURES	Excellent puncture resistance with good oxygen/moisture barrier All materials comply with FDA direct food contact regulations (PET: 21 C.F.R. § 177.1630, mLLDPE: 21 C.F.R. § 177.1520) MET-PET is chemically stable and resistant to attack by oils, solvents, weak acids, and weak alkalis mLLDPE provides strong seal-to-self fusion with low activation temperature mLLDPE has slip additive for reduced friction on packaging equipment		LAMINATE PRINT LAYER LAYER SEALAI (Gloss PET) (CT MET-PET) (Clear mLL	
TYPICAL PROPERTIES	PROPERTY	TYPICAL VALUE	TESTING STANDARD(S)	
	Total Average Thickness (Composite)	4.8 mil	GB/T 6672 (Laminate layer) ASTM F2251 (Print + sealant layers)	
	Thickness Tolerance	±10 %		
	Yield (Composite)	5,836 in²/lb		
	COF (Coefficient of Friction)	≤ 0.5 (Laminate/exterior surface) 0.20-0.35 (Sealant/interior surface)	ASTM D1894	
	Haze (Laminate layer)	≤10 %	ASTM D1003	
	Gloss (45°, laminate layer)	≥70 %	GB/T 8807	
		250-350 °F		

THE PACKAGING LAB

CUSTOM PACKAGING MADE SIMPLE

The information provided here is believed to be correct to the best of our knowledge. This information is provided only as a guide, and does not express or imply any guarantees or warranty. It is your responsibility to evaluate the suitability of this material for your intended use prior to using this product. The Packaging Lab assumes no responsibility for the results of use of the products and processes described here. The Packaging Lab reserves the right to modify product properties or composition at any time without notice.

120-180 °C

50-80 °F

10-26 °C

30-70 %

≥7 lb/in

≤0.03 cm³/100 in²/24 hr

≤0.13 g/100 in²/24 hr

12 mo from delivery

ASTM F88

ASTM D3985

ASTM F1249