
FILM SPECIFICATIONS

MEDIUM GAUGE METALLIZED GLOSS — Rollstock Only







PROPERTY	TYPICAL VALUE	TESTING STANDARD(S)
Total Average Thickness (Composite)	3.3 mil	GB/T 6672 (Laminate layer) ASTM D2103 (Print + sealant layers)
Thickness Tolerance	±10 %	
Yield (Composite)	8,274 in²/lb	
COF (Coefficient of Friction)	≤ 0.5 (Laminate/exterior surfac ≤ 0.2 (Sealant/interior surface)	ASTM D1894
Haze (Laminate layer)	≤10 %	ASTM D1003
Gloss (45°, laminate layer)	≥70 %	GB/T 8807
Seal/Application Temperature (Sealant layer)	250-350 °F 120-180 °C	
Seal Strength (Self-to-self, sealant layer)	≥7 lb/in	ASTM F88
OTR (Oxygen Transmission Rate)	≤0.1 cm³/100 in²/24 h	r ASTM D3985
WVTR (Water Vapor Transmission Rate)	≤0.1 g/100 in²/24 hr	ASTM F1249
Film Shelf Life	12 mo from deliver	у
Storage Temperature Range	50-80 °F 10-26 °C	
Storage Humidity Range	30–70 %	

The information provided here is believed to be correct to the best of our knowledge. This information is provided only as a guide, and does not express or imply any guarantees or warranty. It is your responsibility to evaluate the suitability of this material for your intended use prior to using this product. The Packaging Lab assumes no responsibility for the results of use of the products and processes described here. The Packaging Lab reserves the right to modify product properties or composition at any time without notice.