## FILM SPECIFICATIONS

## THE PACKAGING LAB CUSTOM PACKAGING MADE SIMPLE

## THICK GAUGE CLEAR GLOSS — Pouches & Rollstock

ESCRIPTIO

This film is ideal for durable applications requiring oxygen/moisture barrier properties and puncture resistance.

Clear film can create transparent product windows and/or translucent color effects in printed artwork.

Gloss finish has high shine, and minimal color distortion of printed artwork. Gloss clear film will give product windows a clear view inside.

Evaluation and fitness-for-use is the sole responsibility of the customer.

RUCTURE

Composite: 4.8mil 3-layer laminated film

- Laminate (Exterior) Layer: 1.2mil gloss PET (Polyethylene Terephthalate)
- Print Surface Layer: 48ga CT PET (Corona-Treated PET)
- Sealant (Interior) Layer: 3.0mil clear EVOH (Ethylene-Vinyl Alcohol Copolymer)

ATURE

- Excellent puncture resistance with good oxygen/moisture barrier
- All materials comply with FDA direct food contact regulations (PET: 21 C.F.R. § 177.1630, EVOH: 21 C.F.R. § 177.1360)
- PET is chemically stable and resistant to attack by oils, solvents, weak acids, and weak alkalis
- EVOH provides strong seal-to-self fusion with low activation temperature
- EVOH has slip additive for reduced friction on packaging equipment



F	
PRO	
Z PL	
Ĕ	

PROPERTY	TYPICAL VALUE	TESTING STANDARD(S)
Total Average Thickness is	4.8 mil	GB/T 6672 (Laminate layer)
Total Average Thickness (Composite)		ASTM F2251 (Print + sealant layers)
Thickness Tolerance	±10 %	
Yield (Composite)	5,840 in²/lb	
COF (Coefficient of Friction)	≤0.5 (Laminate/exterior surface)	ASTM D1894
COF (Coefficient of Friction)	0.20-0.35 (Sealant/interior surface)	
Haze (Laminate layer)	≤10 %	ASTM D1003
Gloss (45°, laminate layer)	≥70 %	GB/T 8807
Cool/Application Temporature	250-350 °F	
Seal/Application Temperature (Sealant layer)	120-180 °C	
Seal Strength (Self-to-self, sealant layer)	≥9 lb/in	ASTM F88
OTR (Oxygen Transmission Rate)	≤0.06 cm <sup>3</sup> /100 in <sup>2</sup> /24 hr	ASTM D3985
WVTR (Water Vapor Transmission Rate)	≤0.063 g/100 in²/24 hr	ASTM F1249
Film Shelf Life	12 mo from delivery	
Storage Temperature Bongs	50-80 °F	
Storage Temperature Range	10-26 °C	
Storage Humidity Range	30-70 %	